

Styropor® P 656



Application

For the production of expanded particles as a filling material for lightweight plasters and bitumen sealing compounds.

Product description

Expandable polystyrene (EPS).
Blowing agent: pentane (~6.0%).

Form as supplied

Styropor® P 656 is supplied in the form of rounded particles.

Product	Bead size range	Typical bead size
Styropor® P 656	0.2-0.4 mm	0.2-0.5 mm ≥90 % by weight

Storage

Styropor® P 656 is usually supplied in cardboard containers (octabins). It can be stored in these unopened receptacles for three months before processing.

The octabins should not be exposed to weather conditions (rain, water, snow, frost, and sunlight) and must be protected from damage. They should always be stored in a cool place (below 20°C if possible) to minimize loss of blowing agent.

Once containers have been opened, their contents should be used as soon as possible. In the meantime the octabins should be kept tightly sealed.

It is not recommended to stack octabins more than one layer high. In case of double-stacking octabins under controlled conditions, a strong plywood board must be placed between the stacked containers.

Octabins covered with a plastic hood and/or shrink-wrapped should never be double stacked.

Processing

Styropor® P 656 is expanded to form filling material for lightweight plasters and bitumen sealing compounds.

■ Preexpansion

Attainment of the lowest bulk density is largely dependent on the type and mode of operation of the preexpander.

For the production of lightweight plasters and bitumen sealing compounds the usual bulk density range of 12-25 kg/m³ is reliably controlled in technically sound, discontinuously operating installations.

■ Aging

Aging for at least 6 hours is recommended prior to further processing as a filling material for lightweight plasters.

Safety notes

It should be noted, that during the processing and storage of Styropor®, as well as of foams produced from it, explosive blowing agent/air mixtures may be formed by diffusing blowing agent (pentane, LEL 1.3 vol%).

Therefore, adequate ventilation must be provided at all times. All conceivable ignition sources (open flames, welding sparks, electrical sparks etc.) must be kept away and electrostatic charging must be avoided. Smoking must be strictly prohibited!

The contents of open containers should be processed quickly. At other times the containers are to be kept well sealed. The transportation of Styropor® or of expanded foams freshly made from it in unventilated or closed means of conveyance is not permissible. Further information is included in the respective product safety data sheet.

Biological action

During the storage and in the processing of Styropor® pentane escapes. Especially when cutting the expanded foams with heated wires care is to be taken to remove the vapors arising by suction, since apart from pentane they also contain small amounts of styrene.

The maximum allowable concentration values for styrene and for pentane are to be observed.

Expanded foams made from Styropor® have been manufactured and processed for several decades. In this time no effects harmful to health whatsoever have been ascertained.

Food legislation

For additional information pertaining to the food legislation please contact the local BASF representative.

Note

The information in this publication is based on our current knowledge and experience. This information does not relieve processors of the need to carry out their own tests and trials due to the profusion of possible effects when processing and applying our products. No legally binding assurance of certain properties or of suitability for a specific purpose can be inferred from our information. Recipients of our products are themselves responsible for observing any proprietary rights and existing laws and regulations.